



## Type 2734 – Product Technical Data

### Needle Felt, Thermal Bonded, Laminated Nonwoven

Composition	
Polyester	
Polypropylene	
SAF™	
Polyester / Polypropylene Laminate, Top and Bottom	
Physical Characteristics	
Core Weight (g/m <sup>2</sup> )	180
Laminate Weight (g/m <sup>2</sup> )	40
Total Weight (g/m <sup>2</sup> )	260
Thickness (mm)	2.0
Absorbency (0.9% Saline)	
Absorbent capacity (g/g)	10
Absorbent volume (g/m <sup>2</sup> )	>2,600
Absorbency (DM Water)	
Absorbent capacity (g/g)	18
Absorbent volume (g/m <sup>2</sup> )	>4,600
Other Aspects	
Contamination	Free of contamination as far as practicable

All tests are carried out in accordance with standard protocols.

This document does not constitute a specification for the above material, it is provided as an indication only.

### Contact details

Technical Absorbents Ltd  
1 Moody Lane, Great Coates, Grimsby  
North East Lincolnshire DN31 2SS United Kingdom

[www.techabsorbents.com](http://www.techabsorbents.com)

**T** +44(0) 1472 245200  
**E** [sales@techabsorbents.com](mailto:sales@techabsorbents.com)