



## Product Technical Data / Product Type: 112/52/10

### Absorbency (g/g)

|  |      |
|--|------|
| 15 Minute Free Swell Capacity (0.9% Saline): | 57   |
| 15 Minute Free Swell Capacity (DM):          | >160 |
| 0.3 psi Absorption Under Load (0.9% Saline): | 19   |
| 0.3 psi Absorption Under Load (DM):          | >95  |

### Physical Properties

|                       |                  |
|-----------------------|------------------|
| Colour:               | White            |
| Staple Length (mm):   | 50               |
| Moisture Content (%): | 14% (Typical)    |
| Count (dtex):         | 9 (Mean value)   |
| pH (Saline Extract):  | 5.5 (Mean value) |

### Other Aspects

|            |   |
|------------|---|
| Packaging: | Bales, wrapped and sealed in polypropylene. Each labelled to show: <ul style="list-style-type: none"><li>• Fibre type</li><li>• Unique bale identification number</li><li>• Bale weight</li></ul> |
|------------|---|

### Additional notes

- All tests are carried out in accordance with Technical Absorbents Standard Test Methods which are available upon request.
- All absorbency specifications are quoted on dry fibre.

#### Technical Absorbents Ltd.

1 Moody Lane, Great Coates, Grimsby,  
North East Lincolnshire, DN31 2SS. United Kingdom

☎ +44 (0)1472 245200 ✉ info@exploreSAF.com

exploreSAF.com

a Technical Absorbents product