



## Product Technical Data / SAF™ Spun Yarn: SY-26000

Composition	
SAF™	
Polyester	
Polyamide	

Yarn Count	
Denier	26000
Dtex	28900
Nm	0.35

Physical properties	
Dry diameter (mm)	4.0
Minimum breaking strength (N)	70
Maximum Breaking Extension (%)	12
Moisture Content (%)	<10

Absorbency data (DM Water)	
Minimum Absorbency (g/g)	48
Minimum Absorbency (g/m)	139

All tests are carried out in accordance with standard protocols.

This document does not constitute a specification for the above material, it is provided as an indication only only

### Technical Absorbents Ltd.

1 Moody Lane, Great Coates, Grimsby,  
North East Lincolnshire, DN31 2SS. United Kingdom

☎ +44 (0)1472 245200 ✉ info@exploresAF.com

[exploresAF.com](http://exploresAF.com)

a Technical Absorbents product