



Product Technical Data / Product Type: 2644

Fabric Type	
Air laid, Thermal Bonded, Laminated Nonwoven	

Composition	
Fluff Pulp	
BiCo Fibre	
SAF™	
BiCo Layer Top	
Nonwoven Laminate Bottom	

Physical Characteristics	
Weight (g/m ²)	345
Thickness (mm)	3.5

Absorbency (0.9% Saline)	
Absorbent capacity (g/g)	29
Absorbent volume (g/m ²)	>10,000

Absorbency (DM Water)	
Absorbent capacity (g/g)	77
Absorbent volume (g/m ²)	>26,500

All tests are carried out in accordance with standard protocols.

This document does not constitute a specification for the above material, it is provided as an indication only.

Technical Absorbents Ltd.

1 Moody Lane, Great Coates, Grimsby,
North East Lincolnshire, DN31 2SS. United Kingdom

☎ +44 (0)1472 245200 ✉ info@exploreSAF.com

exploreSAF.com

a Technical Absorbents product