



Product Technical Data / Product Type: 2715

Fabric Type	
Air Laid, Thermal Bonded, Laminated Nonwoven	

Composition	
SAF™	
Fluff pulp	
Bicomponent fibre	

Physical Characteristics	
Weight (g/m ²)	500
Thickness (mm)	>6.2

Absorbency (0.9% Saline)	
Absorbent capacity (g/g)	20
Absorbent volume (g/m ²)	>10,300

Absorbency (DM Water)	
Absorbent capacity (g/g)	30
Absorbent volume (g/m ²)	>15,400

All tests are carried out in accordance with standard protocols.

This document does not constitute a specification for the above material, it is provided as an indication only.

Technical Absorbents Ltd.

1 Moody Lane, Great Coates, Grimsby,
North East Lincolnshire, DN31 2SS. United Kingdom

☎ +44 (0)1472 245200 ✉ info@exploreSAF.com

exploreSAF.com

a Technical Absorbents product